

RESIN BOUND TYPICAL FLOW RATE

Permeability - Approx. water flow rates for RESIN BOUND and ALTIDRIVE TARMAC products.

Nominal Size (mm)	Aggregate Type	Application	Approximate Flow Rate
	Permeable Tarmac	Pedestrian	9 l/m ² /hour
		Vehicular	9 l/m ² /hour
10mm	Gravel	Tree pit	78 l/m ² /sec
		Pedestrian	78 l/m ² /sec
		Vehicular	78 l/m ² /sec
	Crushed Rock	Tree pit	96 l/m ² /sec
		Pedestrian	96 l/m ² /sec
		Vehicular	73 l/m ² /sec
6mm	Gravel	Tree pit	60 l/m ² /sec
		Pedestrian	30 l/m ² /sec
		Vehicular	22 l/m ² /sec
	Crushed Rock	Tree pit	53 l/m ² /sec
		Pedestrian	53 l/m ² /sec
		Vehicular	25 l/m ² /sec
3mm	Gravel	Pedestrian	25 l/m ² /sec
		Vehicular	19 l/m ² /sec
	Crushed Rock	Pedestrian	18 l/m ² /sec
		Vehicular	16 l/m ² /sec